Repair System for Protection Against Abrasive Attack





Belzona 1814 is a cost-effective three-component repair system for the protection of surfaces subject to abrasive attack.

This material is designed to provide protection in highly abrasive environments and is specifically formulated for application over large areas.

Supplied as a three-part system, with a base, solidifier and aggregate, Belzona 1814 is easy to mix and apply without the need for specialist tools.

This thixotropic material will adhere to a wide range of substrates, providing a seamless abrasion resistant lining at thicknesses up to 12.7mm (1/2in).

| | Mixing ratio (base : solidifier : aggregate) | 2:1:5 by volume | | | |
|----------------|----------------------------------------------|--------------------------------------------------|--------------------------------------|--|--|
| TECHNICAL DATA | Working life | 60 minutes at 20°C (68°F) | | | |
| | Coverage rate | 4.27 m² (46 ft²) at 3mm (0.12 in) per 30 kg unit | | | |
| | Shelf life | 5 years | | | |
| | Taber Dry (CS17) 1kg 1000 cycles | 11 mm³ loss | | | |
| | Taber Wet (H10) 1kg 1000 cycles | 107 mm³ loss | | | |
| | Grit Impact 2kg 90° 80 psi | 17 mm³ loss | | | |
| | Heat distortion temperature (HDT) | 43°C (109°F) after 20°C (68°F) cure | 75°C (167°F) after 90°C (194°F) cure | | |
| | Adhesion (Tensile Shear) | Mild Steel: 6.6 MPa (960 psi) | | | |

| ВS | Temperature | 10°C (50°F) | 20°C (68°F) | 30°C (86°F) | 40°C (104°F) |
|---------|--------------------------------------|-------------|-------------|-------------|--------------|
| Σ - | Movement or use involving no loading | 32 hours | 12 hours | 10 hours | 6 hours |
| ш | Light loading | 5 days | 24 hours | 16 hours | 12 hours |
| _ | Full mechanical or thermal loading | 14 days | 7 days | 4 days | 2 days |

^{*}Please consult the Product Specification Sheet (PSS) and Instructions for Use (IFU) for the latest technical data.







SOLVENT FREE



EASY TO APPLY OVER LARGE AREAS

BELZONA 1814



Key Benefits:

• Excellent abrasion resistance

Belzona 1814 exhibits outstanding abrasion resistance and can withstand dry abrasion up to temperatures of 75°C (167°F).

Easy to apply


The material is easy to mix and benefits from extended working life making it ideal for large areas. During application, no specialist tools are necessary and it is possible to apply thick and thin sections in one operation.

• Impressive adhesive properties

Belzona 1814 can bond to all rigid substrates, including steel and cast iron.

Seamless finish


It is a seamless solvent-free material which upon curing will not shrink, expand or distort.



Protection for chutes and hoppers



Simple mixing



Grouting for alumina tiles



Easy application

Application Areas:

- Slurry pumps
- Chutes
- Hydrocyclones
- Grinding mills
- Conveying systems
- Mining industry
- Dredging vessels
- Coal power
- Pulp and paper
- Cement
- Sugar industry



For more information, please contact your local Belzona representative:

QUALITY PRODUCTS - TECHNICAL SUPPORT

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

Belzona has a global distribution network of over 140 Distributors operating in 120 countries. Local support is provided by a trained Technical Consultant who will diagnose the problem, recommend the solution and provide 24-hour, on-site application supervision and advice.